

04-30-01

U.S. Application No.  
60/200,219International Application No.  
PCT/IB99/01747Attorney Docket No.  
JKERN14.001APC

PCT

Date: April 27, 2001

09/830855 Page 1

JC07 Rec'd PCT/PTO 27 APR 2001

TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US)  
CONCERNING A FILING UNDER 35 USC 371


International Application No.: PCT/IB99/01747  
 International Filing Date: October 29, 1999  
 Priority Date Claimed: October 29, 1998  
 Title of Invention: ASSAYING  
 Applicant(s) for DO/EO/US: Willem Hendrik Brits

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 USC 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 USC 371.
3. ☒ This express request to begin national examination procedures (35 USC 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 USC 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 USC 371(c)(2))
  - a) ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b) ☒ has been transmitted by the International Bureau.
  - c) ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ A translation of the International Application into English (35 USC 371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 USC 371(c)(3))
  - a) ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
  - b) ☐ have been transmitted by the International Bureau.
  - c) ☐ have not been made; however, the time limit for making such amendments has NOT expired.
  - d) ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 USC 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 USC 371(c)(4)).
10. ☒ A copy of the International Preliminary Examination Report with any annexes thereto, such as any amendments made under PCT Article 34.
11. ☐ A translation of the annexes, such as any amendments made under PCT Article 34, to the International Preliminary Examination Report under PCT Article 36 (35 USC 371(c)(5)).

04/27/01  
 J1052 U.S. PTO

9830855-042701



U.S. Application No.  
60/200,219

International Application No.  
PCT/IB99/01747

Date: April 27, 2001

Page 2

**Items 11. to 16. below concern other document(s) or information included:**

- 12.    ☐     An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
- 13.    ☒    An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
- 14.    ☒    A FIRST preliminary amendment.  
         ☐     A SECOND or SUBSEQUENT preliminary amendment.
- 15.    ☐     A substitute specification.
- 16.    ☐     A power of attorney and/or address letter.
- 17.    ☒    International Application as published.
- 18.    ☐     Other Items or Information:
- 19.    ☐     PCT Form PCT/IPEA/402.
- 20.    ☐     PCT Form PCT/IB/308.
- 21.    ☒    PCT request form.
- 22.    ☒    A return prepaid postcard.
- 23.    ☒    The following fees are submitted:

				FEES
<b>BASIC FEE</b>				\$860
<b>CLAIMS</b>	<b>NUMBER FILED</b>	<b>NUMBER EXTRA</b>	<b>RATE</b>	
Total Claims	37 - 20 =	17 ×	\$18	\$306
Independent Claims	1 - 3 =	0 ×	\$80	\$0
Multiple dependent claims(s) (if applicable)			\$270	\$0
<b>TOTAL OF ABOVE CALCULATIONS</b>				\$1166
Reduction by 1/2 for filing by small entity (if applicable). Verified Small Entity statement must also be filed. (NOTE 37 CFR 1.9, 1.27, 1.28)				\$*
<b>TOTAL NATIONAL FEE</b>				\$1166
<b>TOTAL FEES ENCLOSED</b>				\$1166

09/830855-042701

U.S. Application No.  
60/200,219

International Application No.  
PCT/IB99/01747

09/830855  
JC18 Rec'd PCT/IB 27 APR 2001  
Attorney Docket No.  
JKERN14.001APC

Date: April 27, 2001

Page 3

24. (X) A check in the amount of \$1166 to cover the above fees is enclosed.
25. (X) Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40 per property.
26. (X) The Commissioner is hereby authorized to charge only those additional fees which may be required, now or in the future, to avoid abandonment of the application, or credit any overpayment to Deposit Account No. 11-1410.

27. (X) A check in the amount of \$40.00 for assignment fee is enclosed

**NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.**

SEND ALL CORRESPONDENCE TO:

KNOBBE, MARTENS, OLSON & BEAR, LLP  
620 Newport Center Drive  
Sixteenth Floor  
Newport Beach, CA 92660

  
Signature

Karoline A. Delaney  
Printed Name

44,058  
Registration Number

H:\DOCS\KAD\KAD-4921.DOC  
042701

09/830855-042701


09/830855

JC18 Rec'd PCT/PTO 2 7 APR 2001

JKERN14.001APC

PATENT

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant	:	Brits, Willem Hendrik	)	Group Art Unit Unknown
Appl. No.	:	Unknown (corresponding to PCT Application Number PCT/IB99/01747	)	I hereby certify that this correspondence and all marked attachments are being deposited with the United States Postal Service as first-class mail in an envelope addressed to: Assistant Commissioner for Patents, Washington, D.C. 20231, on
Filed	:	Herewith	)	
For	:	ASSAYING	)	April 27, 2001 (Date)
Examiner	:	Unknown	)	 Karoline A. Delaney, Reg. No. 44,058

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents  
Washington, D.C. 20231

Dear Sir:

Prior to examination on the merits, please amend the above-captioned application as follows.

IN THE SPECIFICATION

Please add the following paragraph and heading, immediately following the title, as follows:

Cross-Reference to Related Applications

This application is a national phase application under 35 U.S.C. § 371 of PCT Application Serial Number PCT/IB99/01747 filed on October 29, 1999 which claims priority to South African Application Serial Number 98/9866 filed on October 29, 1998 the disclosures of which are incorporated herein by reference in their entireties.

Please replace the paragraph beginning at page 9, line 16, with the following rewritten paragraph:

Detailed Description of the Preferred Embodiments

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

Please replace the paragraph beginning at page 11, line 16, with the following rewritten paragraph:

In the process, the lid 28 of the bottle 20 is removed an aliquot sample of ore is added to a bottle 20 containing flux 26, the lid 28 is applied back onto the bottle 20 and the sample and flux is combined by merely shaking the bottle.

Please replace the paragraph beginning at page 12, line 10, with the following rewritten paragraph:

Referring to Figure 3, bottles 2 which contain ore sample combined with flux are loaded onto a sample loader 34 which comprises a conveyor belt 36, an optical sensor 38, a bar code reader 40, and a mechanical gripper arm 42. In use, the optical sensor 38 senses the presence of a bottle 20, the bar code reader 40 (positioned above the bottle, and shown in dotted outline) scans the bar code 28 on the lid 22 of the bottle 20 and the gripper arm 42 grips the bottle at the ridge 30 and transfers it into an induction furnace 44 which is powered by a generator 46. The conveyor 36 conveys the next bottle 20 in line with the sensor 38 and this next bottle is then ready to be transferred into the induction furnace 44. Once placed in the induction furnace 44, the identity of the bottle 20 is compared to the information stored on the central database and the bottle 20 is heated at a temperature profile that corresponds to the ore sample and flux contained within the bottle 20.

Please replace the paragraph beginning at page 13, line 26, with the following rewritten paragraph:

In a typical example where the temperature profile is kept constant, the melting pot 26 is heated to about 900° and the flux and sample is inserted into the melting pot 26. The coil 48 is supplied with 15-30 kW of electrical energy from the generator 46 for a predetermined first period of time (usually 20 to 30 seconds) to heat the pot to about 1250°C and then dropped to 10 to 12kW for a predetermined second period of time (usually 20 to 30 seconds), maintaining the temperature of the melting pot about 1250°C. Thus, fusion of the ore and flux takes from 45 to 90 seconds, generally approximately 60 seconds.

Please replace the paragraph beginning at page 15, line 21, with the following rewritten paragraph:

The advantage of the flux 26 over known flux compositions is that the sodium hydroxide has a melting point of 318°C, which is much lower than the melting point of CaCO<sub>3</sub>, used in

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

conventional fire assay processes. Thus, when the flux 26 is added to the crucible 46 in the induction furnace 44 (which is normally preheated a temperature of about 1000°C), the sodium hydroxide melts, wets the sample and flux, and retards spattering and boiling when power is applied to the induction furnace. The sodium hydroxide then reacts with silicates in the sample to form slag. Up to now it has not been possible to use sodium hydroxide in conventional fire assay processes as these processes make use of clay pots and the sodium hydroxide would react with silica-in the pots and destroy them during heating. The sodium hydroxide does not however have this effect on a graphite or zirconium melting pot 46. Also, there has been no feasible way of storing and transporting NaOH, because it is hygroscopic, and the sealed containers calcium carbonate cannot be used in an induction furnace as it will blow out during rapid heating of the melting pot 46.

Please add the following paragraph beginning at page 21, line 4:

**Examples**

**IN THE CLAIMS**

Please amend Claims 1, 5, 7, 9-12, 15-24, 26-37 as follows:

**What is Claimed:**

1. (Amended) A method of assaying an ore sample to determine the concentration of selected metals therein, comprising the steps of:

combining the prepared ore sample with a lead-containing flux in a receptacle;  
inductively heating the combination to form a fusion of slag and lead, the lead  
collecting the metals in the sample; and  
separating the lead from the slag.

5. (Amended) The method according to Claim 1 wherein the sample of ore and flux are combined in a container made from carbon-based material, and the container, the sample and the flux are inductively heated.

7. (Amended) The method according to Claim 5 wherein the container includes identification means for identifying the sample contained therein.

9. (Amended) A method according to Claim 1 wherein the flux contains sodium hydroxide.

10. (Amended) The method according to Claim 1 wherein the sample is heated inductively within a graphite receptacle in an induction furnace.

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

11. (Amended) The method according to Claim 1 wherein the sample is heated inductively within a zirconium receptacle in an induction furnace.

12. (Amended) The method according to Claim 1 wherein molten lead separated from the slag is poured into a chilled mould, to provide a solid lead button.

15. (Amended) A method according to Claim 12 wherein each solid lead button is stamped with an identification code.

16. (Amended) A receptacle for use in a method of assaying an ore sample according to Claim 1, the receptacle comprising a base with a side wall extending from the base, the side wall defining a top opening into the receptacle, and the side wall having a collecting cavity, wherein the collecting cavity is sized to collect a predetermined amount of molten lead.

17. (Amended) A receptacle for use in a method of assaying an ore sample according to Claim 16 wherein the collecting cavity is located proximate the top opening of the receptacle.

18. (Amended) A receptacle for use in a method of assaying an ore sample according to Claim 16 wherein barrier means is provided between the collecting cavity and the opening of the receptacle, to trap molten lead in the collecting cavity.

19. (Amended) A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim 16 wherein the collecting cavity is formed within a removable plug which is attachable to the side wall of the receptacle.

20. (Amended) A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim 16 including a first spout located at the top opening, above the collecting cavity.

21. (Amended) A receptacle for use in a method of assaying an ore sample according to Claim 20 including a second spout located at the top opening, diametrically opposed to the first spout.

22. (Amended) A receptacle for use in a method of assaying an ore sample according Claim 16 wherein the receptacle is also a melting pot for an induction furnace.

23. (Amended) A receptacle for use in a method of assaying an ore sample according Claim 16 made from graphite.

24. (Amended) A method of separating molten lead from slag, in the receptacle of Claim 16, the method including the steps of:

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

1. introducing a slag with a predetermined amount of molten lead therein into the receptacle;
  2. rotating the receptacle in a first direction toward the collecting cavity so that the molten lead fills and is retained within the cavity, rotating the receptacle further so that the slag is discharged from the opening to the receptacle;
  3. rotating the receptacle so that the molten lead flows out of the opening to the receptacle; and
  4. collecting the lead discharged from the opening of the receptacle.
26. (Amended) A flux composition for use in a method of assaying an ore sample according to Claim 1, the flux composition containing sodium hydroxide.
27. (Amended) A flux composition for use in a method of assaying an ore sample according to Claim 26, comprising 20% to 60%, by weight, sodium hydroxide.
28. (Amended) A flux composition for a method ~~for~~of assaying an ore sample according to Claim 26 further comprising:
29. (Amended) A flux composition for use in a method of assaying an ore sample according to Claim 27 comprising 20% to 50%, by weight sodium hydroxide, 25% to 40% lead oxide and 25% to 40% borax.
30. (Amended) A flux composition for use in a method of assaying an ore sample according to Claim 26 further including silver nitrate.
31. (Amended) A sealed container, for use in a method of assaying in an ore sample according to Claim 5, the sealed container made from a carbon-based sodium carbonate.
32. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 31 including a replaceable lid.
33. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 31 made from a combustible material.
34. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 33 made from a plastics material.
35. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 34 made from a mixture of plastics material and a flux material.
36. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 35 wherein the flux material is calcium carbonate.



**Appl. No.** : **Unknown (corresponding to PCT Application Number**  
**PCT/IB99/01747**

**Filed** : **Herewith**

37. (Amended) A sealed container for use in a method of assaying an ore sample according to Claim 36, the mixture including 60 to 80%, by weight, calcium carbonate.

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747  
Filed : Herewith

REMARKS

Claims 1-37 are pending with Claims 1, 5, 7, 9-12, 15-24, 26-37 being amended herein. Applicants believe that none of the foregoing amendments have added new matter to the application.

The specific changes to the specification are shown on a separate set of pages attached hereto and entitled VERSION WITH MARKINGS TO SHOW CHANGES MADE, which follows the signature page of this Amendment. On this set of pages, the insertions are underlined while the ~~deletions are struck through~~.

The foregoing amendments more closely conform the application to U.S. practice. The above requested changes to the application do not add new matter, and entry of the amendments is respectfully requested. If, however, there are any matters which could be resolved by a telephone interview, the Examiner is cordially invited to contact the undersigned by telephone so that any such matters can be promptly resolved.

Respectfully submitted,

KNOBBE, MARTENS, OLSON & BEAR, LLP

Dated:

27 April 2001

By:

Karoline A. Delaney

Karoline A. Delaney

Registration No. 44,058

Attorney of Record

620 Newport Center Drive

Sixteenth Floor

Newport Beach, CA 92660

## VERSION WITH MARKINGS TO SHOW CHANGES MADE

### IN THE SPECIFICATION

The following paragraph has been added, immediately after the title:

#### Cross-Reference to Related Applications

This application claims priority to South African Application Serial Number 98/9866 filed on October 29, 1998 and PCT Application Serial Number PCT/IB99/01747 filed on October 29, 1999, the disclosures of which are incorporated herein by reference in their entireties.

The paragraph beginning at page 1, line 6, has been amended as follows:

#### ~~Description of an Embodiment~~ Detailed Description of the Preferred Embodiments

The paragraph beginning at page 11, line 16, has been amended as follows:

In the process, the lid 28 of the bottle 20 is removed an aliquot sample of ore is added to a bottle 20 containing flux 26, the lid ~~22~~ 28 is applied back onto the bottle 20 and the sample and flux is combined by merely shaking the bottle.

The paragraph beginning at page 12, line 10, has been amended as follows:

Referring to Figure 3, bottles 2 which contain ore sample combined with flux are loaded onto a sample loader 34 which comprises a conveyor belt 36, an optical sensor 38, a bar code reader 40, and a mechanical gripper arm 42. In use, the optical sensor 38 senses the presence of a bottle 20, the bar code reader 40 (positioned above the bottle, and shown in dotted outline) scans the bar code 28 on the lid ~~22~~ of the bottle 20 and the gripper arm 42 grips the bottle at the ridge 30 and transfers it into an induction furnace 44 which is powered by a generator 46. The conveyor 36 conveys the next bottle 20 in line with the sensor 38 and this next bottle is then ready to be transferred into the induction furnace 44. Once placed in the induction furnace 44, the identity of the bottle 20 is compared to the information stored on the central database and the bottle 20 is heated at a temperature profile that corresponds to the ore sample and flux contained within the bottle 20.

The paragraph beginning at page 13, line 26, has been amended as follows:

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

In a typical example where the temperature profile is kept constant, the melting pot 46 26 is heated to about 900° and the flux and sample is inserted into the melting pot 46 26. The coil 48 is supplied with 15-30 kW of electrical energy from the generator 46 for a predetermined first period of time (usually 20 to 30 seconds) to heat the pot to about 1250°C and then dropped to 10 to 12kW for a predetermined second period of time (usually 20 to 30 seconds), maintaining the temperature of the melting pot about 1250°C. Thus, fusion of the ore and flux takes from 45 to 90 seconds, generally approximately 60 seconds.

The paragraph beginning at page 15, line 21, has been amended as follows:

The advantage of the flux 26 over known flux compositions is that the sodium hydroxide has a melting point of 318°C, which is much lower than the melting point of CaCO<sub>3</sub>, used in conventional fire assay processes. Thus, when the flux 26 is added to the crucible 46 in the induction furnace 46 44 (which is normally preheated a temperature of about 1000°C), the sodium hydroxide melts, wets the sample and flux, and retards spattering and boiling when power is applied to the induction furnace. The sodium hydroxide then reacts with silicates in the sample to form slag. Up to now it has not been possible to use sodium hydroxide in conventional fire assay processes as these processes make use of clay pots and the sodium hydroxide would react with silica-in the pots and destroy them during heating. The sodium hydroxide does not however have this effect on a graphite or zirconium melting pot 46. Also, there has been no feasible way of storing and transporting NaOH, because it is hygroscopic, and the sealed containers calcium carbonate cannot be used in an induction furnace as it will blow out during rapid heating of the melting pot 46.

The paragraph beginning at page 21, line 4, has been added as follows:

### Examples

### IN THE CLAIMS

The paragraph beginning at page 27, line 1, has been amended as follows:

### Claims What is Claimed:

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

1. A method ~~for~~of assaying an ore sample to determine the concentration of selected metals therein, comprising the steps of:

combining the prepared ore sample with a lead-containing flux in a receptacle;

inductively heating the combination to form a fusion of slag and lead, the lead

collecting ~~containing~~ the metals in the sample; and

separating the lead from the slag.

5. The method according to ~~any one of the preceding claims~~ Claim 1 wherein the sample of ore and flux are combined in a container made from carbon-based material, and the container, the sample and the flux are inductively heated.

7. The method according to Claim 5 ~~or 6~~ wherein the container includes identification means for identifying the sample contained therein.

9. A method according to ~~any one of the preceding claims~~ Claim 1 wherein the flux contains sodium hydroxide.

10. The method according to ~~any one of the preceding claims~~ Claim 1 wherein the sample is heated inductively within a graphite receptacle in an induction furnace.

11. The method according to ~~any one of the preceding claims~~ Claim 1 wherein the sample is heated inductively within a zirconium receptacle in an induction furnace.

12. The method according to ~~any one of the preceding claims~~ Claim 1 wherein molten lead separated from the slag is poured into a chilled mould, to provide a solid lead button.

15. A method according to ~~one of the preceding claims~~ Claim 12 wherein each solid lead button is stamped with an identification code.

16. A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim 1, the receptacle comprising a base with a side wall extending from the base, the side wall

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

defining a top opening into the receptacle, and the side wall having a collecting cavity, wherein the collecting cavity is sized to collect a predetermined amount of molten lead.

17. A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim 16 wherein the collecting cavity is located proximate the top opening of the receptacle.

18. A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim ~~16 or~~ 17 wherein barrier means is provided between the collecting cavity and the opening of the receptacle, to trap molten lead in the collecting cavity.

19. A receptacle for use in a method ~~for~~of assaying an ore sample according to ~~any one of claims~~ Claim 16 ~~to 18~~ wherein the collecting cavity is formed within a removable plug which is attachable to the side wall of the receptacle.

20. A receptacle for use in a method ~~for~~of assaying an ore sample according to ~~any one of Claims~~ Claim 16 ~~to 19~~ including a first spout located at the top opening, above the collecting cavity.

21. A receptacle for use in a method ~~for~~of assaying an ore sample according to Claim 20 including a second spout located at the top opening, diametrically opposed to the first spout.

22. A receptacle for use in a method ~~for~~of assaying an ore sample according to ~~any one of Claims~~ Claim 16 ~~to 21~~ wherein the receptacle is also a melting pot for an induction furnace.

23. A receptacle for use in a method ~~for~~of assaying an ore sample according to ~~any one of Claims~~ Claim 16 ~~to 22~~ made from graphite.

24. A method ~~for~~of separating molten lead from slag, in the receptacle of Claim 16, the method including the steps of:

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

1. introducing a slag with a predetermined amount of molten lead therein into the receptacle;
  2. rotating the receptacle in a first direction toward the collecting cavity so that the molten lead fills and is retained within the cavity, rotating the receptacle further so that the slag is discharged from the opening to the receptacle;
  3. rotating the receptacle so that the molten lead flows out of the opening to the receptacle; and
  4. collecting the lead discharged from the opening of the receptacle.
26. A flux composition for use in a method ~~for~~of assaying an ore sample according to Claim 1, the flux composition containing sodium hydroxide.
27. A flux composition for use in a method ~~for~~of assaying an ore sample according to Claim 26, comprising 20% to 60%, by weight, sodium hydroxide.
28. A flux composition for a method ~~for~~of assaying an ore sample according to ~~any one of Claims~~ Claim 26 ~~to 27~~ further comprising:
29. A flux composition for use in a method ~~for~~of assaying an ore sample according to Claim 27 comprising 20% to 50%, by weight sodium hydroxide, 25% to 40% lead oxide and 25% to 40% borax.
30. A flux composition for use in a method ~~for~~of assaying an ore sample according to ~~any one of Claims~~ Claim 26 ~~to 29~~ further including silver nitrate.
31. A sealed container, for use in a method ~~for~~of assaying in an ore sample according to Claim 5, the sealed container made from a carbon-based sodium carbonate.
32. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 31 including a replaceable lid.

Appl. No. : Unknown (corresponding to PCT Application Number  
PCT/IB99/01747

Filed : Herewith

33. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 31 ~~or 32~~ made from a combustible material.

34. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 33 made from a plastics material.

35. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 34 made from a mixture of plastics material and a flux material.

36. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 35 wherein the flux material is calcium carbonate.

37. A sealed container for use in a method ~~for~~of assaying an ore sample according to Claim 36, the mixture including 60 to 80%, by weight, calcium carbonate.



WO 00/26664

09/830855

PCT/IB99/01747  
JC18 Rec'd PCT/PTO 27 APR 2001

4/PRTS

- 1 -

ASSAYINGBACKGROUND OF THE INVENTION

This invention relates to assaying.

In order to plan and manage mining operations and to estimate recoverable ore reserves it is necessary to have the facility to determine the concentration in ore samples of precious metals, typically gold and PGMs (platinum group metals including platinum, palladium, rhodium, osmium, indium and ruthenium). It is already known to use a fire assay process for this purpose. In fire assay, PGMs and gold are separated from gangue materials by collection into either lead or nickel sulphide at temperatures of around 1200 - 1450°C. This is achieved by mixing an aliquot of the sample with a flux containing either lead oxide, for the lead collection, or a combination of nickel carbonate and sulphur, for the nickel sulphide, with other chemicals. A flux containing lead oxide which has been found to work satisfactorily in the conventional fire assay method consists of calcium carbonate, lead oxide, borax and silica, and a carbon source such as activated carbon, maize meal or flour. This mixture is placed into a ceramic crucible, which in turn is placed into an electric or gas fired furnace and heated to an appropriate temperature for a period of about 90 minutes. During this time the mixture melts and, because their chemical affinity, PGMs and gold are collected into either lead or nickel sulphide. On cooling the lead or nickel sulphide is separated from the gangue material and the PGMs and gold content determined by a number of analytical techniques.

TO 2349 550860

WO 00/26664

PCT/IB99/01747

- 2 -

The advantage of Fire Assay collection over other analytical procedures is that it effectively concentrates PGMs and gold from a large sample aliquot into a media which is much more amenable to further treatment for the separation and analysis of the PGMs and gold. Fire Assay is, therefore, used extensively in all laboratories engaged in the analysis of samples containing precious metals and, indeed, is an essential stage in the analysis of lower grade samples such as concentrates, feeds and tails.

In electrically heated furnaces, radiant heat from resistive elements is applied to the prepared ore samples. It is difficult to maintain constant operating conditions in an electrical furnace. Furthermore, resistive elements are fragile and deteriorate over time. This variability in furnace conditions detrimentally affects the accuracy of assay results and gives rise to excessive repeat rates.

Gas fired furnaces on the other hand are noisy and require frequent maintenance, which lengthens the average time taken to complete an assay.

The flux used in assaying contains lead and is environmentally hazardous, either in dust form during the flux preparation stage, or as fumes which form during the fusion and cupellation stages of the process. Personnel involved in the assaying process require monitoring of lead blood levels every six months, which is expensive and disconcerting to the persons involved.

The fusion pots used for fusion of the flux / ore sample combinations are brittle and break easily. In order to overcome this difficulty, each assay is duplicated or triplicated, to ensure that at least one successful assay result is

09330355.04241

WO 00/26664

PCT/IB99/01747

- 3 -

obtained, which increases the overall assaying costs. Further, the duplicated or triplicated samples are fused in different furnaces in order to compensate for the variability in furnace conditions.

The recovery of lead from the fusion slag is also hazardous as the slag is broken up, usually manually, by impact to liberate globules of lead entrapped in the slag. Slivers of slag are sharp and necessitate the wearing of adequate safety equipment. Generally, not all lead globules are usually liberated from the slag, leading to an inevitable loss of lead.

Current assay techniques are labour intensive and, therefore, prone to human error. The average time taken to complete an assay normally exceeds twelve hours. It is desired to improve the accuracy, the turnaround time and the safety aspects of known prior art assaying techniques.

#### SUMMARY OF INVENTION

According to a first aspect of the invention there is provided a method for assaying an ore sample to determine the concentration of selected metals therein, comprising the steps of:

preparing an ore sample;

combining the prepared ore sample with a lead-containing flux;

inductively heating the combination typically at a predetermined reference temperature profile to form a fusion of slag and lead containing the metals in the sample;

FOI 2000-0424

**PCT/IB99/01747**

- 4 -

determining the concentration of the selected metals in the sample.

The sample may be supplied with a constant temperature profile, or it may be supplied with a varied temperature profile. For example, the sample is supplied with a high level of heat for a predetermined first period of time and then supplied with a lower level of heat for a predetermined second period of time to form the fusion of slag and lead.

The sample of ore and flux is preferably mixed in a container made from carbon-based material, and the container is inductively heated together with the sample and flux.

Preferably, the container is made from plastics material and comprises a lid which is arranged to close the container sealingly.

The container may also comprise identification means in the form of a bar code for identifying the sample contained therein.

Advantageously, the flux contains sodium hydroxide.

The sample is preferably heated inductively within a graphite or more preferably within a zirconium melting pot in an induction furnace.

- 5 -

Advantageously, molten lead separated from the slag is poured into a chilled mould, to provide a solid lead button.

The solid lead button may then be analyzed by way of spark analysis or laser ablation.

According to a second aspect of the invention there is provided a method as described above including the steps of storing information on each sample on a central database, providing each bottle into which the sample is poured with a unique identification means such as a bar code identifying each bottle, for example by scanning, before inserting it into the induction furnace, correlating the identity of the bottle and information on the central database, and applying a predetermined reference temperature profile to the sample, according to the information on the sample stored in the database.

Preferably, each lead button is stamped with an identification code.

According to a third aspect of the invention there is provided a receptacle for separating molten lead from slag, the receptacle comprising a base with a side wall extending from the base, the side wall defining a top opening into the receptacle, and the side wall having a collecting cavity, wherein the collecting cavity is sized to collect a predetermined amount of molten lead.

Advantageously, the collecting cavity is located proximate the top opening of the receptacle.

Preferably, barrier means is provided between the collecting cavity and the

TO 24/04 '01 16:32 FAX +27 11 3157445 JOHN AND KERNICK

WO 00/26664

PCT/IB99/01747

- 6 -

opening of the receptacle, to trap molten lead in the collecting cavity.

The collecting cavity is preferably formed within a removable plug which is attachable to the side wall of the receptacle.

Advantageously, the receptacle includes a first spout located at the top opening, above the collecting cavity.

The receptacle preferably includes a second spout located at the top opening, diametrically opposed to the first spout.

Advantageously, the receptacle is also a melting pot for an induction furnace.

The receptacle is preferably made from graphite, more preferably zirconium.

According to a fourth aspect of the invention there is provided a method for separating molten lead from slag, in the receptacle described above, the method including the steps of:

1. introducing a slag with a predetermined amount of molten lead therein into the receptacle;
2. rotating the receptacle in a first direction toward the collecting cavity so that the molten lead fills and is retained within the cavity, rotating the receptacle further so that the slag is discharged from the opening to the receptacle;

- 7 -

3. rotating the receptacle so that the molten lead flows out of the cavity and is discharged out of the opening to the receptacle, for example, by rotating the receptacle in a second direction, opposite to the first direction; and
4. collecting the lead discharged from the opening of the receptacle.

Advantageously, the receptacle is a melting pot surrounded by an electromagnetic coil and the electromagnetic coil is rotated together with the melting pot.

According to a fifth aspect of the invention there is provided a flux composition for use in fire assaying of ore samples, the composition containing sodium hydroxide.

Preferably, the flux composition comprises 20% to 60%, more preferably 25% to 40%, by weight, sodium hydroxide.

The composition may further comprise:

- 20% to 60%, preferably 25% to 40%, by weight, lead oxide; and
- 20% to 60%, preferably 25% to 40%, by weight, borax.

Advantageously, the composition may also comprise silver nitrate.

According to a sixth aspect of the invention, there is provided a sealed container, made from a carbon-based material, containing a charge of flux

PCT/IB99/01747

- 8 -

Preferably, the container includes a replaceable lid.

Advantageously, the container is made from a mixture of plastics material and a flux material, such as calcium carbonate.

### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic flow diagram of a process according to the invention for assaying an ore sample to determine the concentration of selected metals therein:

Figure 3 is a schematic top plan view of an apparatus according to the invention for carrying out the process of Figure 1;



- 9 -

Figure 4 is a cross-sectional view of an induction furnace according to the invention;

Figure 5 is a pictorial view of a preferred melting pot according to the invention;

Figure 6 is a cross-sectional view of the melting pot shown in Figure 5, along the line 6-6; and

Figure 7 is a cross-sectional view of the induction furnace shown in Figure 4, shown in two positions in which matter is discharged from the furnace.

#### DESCRIPTION OF AN EMBODIMENT

Referring to Figure 1, according to the invention there is provided a method of assaying an ore sample, the method including the steps of preparing an ore sample 10, mixing the ore sample 10 with a flux 12 which includes lead oxide, to form a mixture 14, inductively heating the mixture 14 to form a fusion of slag 16 and lead 18 containing gold and PGMs, separating the lead 18 from the slag 16 and determining the amount of gold and PGMs in the lead.

In the sample preparation step, an ore sample is logged and its bulk weight determined. The ore sample is then dried, comminuted and sieved and split into a number of aliquots which are deposited into storage containers in the

TO 24/04 '01 16:33 FAX +27 11 3157445 JOHN AND KERNICK

WO 00/26664

PCT/IB99/01747

- 10 -

form of small plastic bottles, each of which already contains a flux.

Information on the sample, such as weight, type etc is entered onto a computer and identification means in the form of a bar code label is produced for each sample. The unused portion of the ore sample is sealed in a storage container and identified by means of a bar code label indicating identification, origin and date of assay.

A typical bottle 20 into which an aliquot ore sample is placed is shown in Figure 2. The bottle 20 is made from a plastics material (polypropylene) and has a lid 22 (made from polyethylene) which engages sealingly with the opening into the bottle 20. A charge of flux 26 is shown in the bottle 20. A charge of flux is a sufficient amount of a particular composition of flux for carrying out the fire assay of an aliquot of a particular ore sample. Each bottle 20 is identified by identification means in the form of a printed bar code label 28 indicative of sample identification and weight, which is attached to the top surface of the lid 22. The bottle is also provided with a ridge 30 just below the lid 22.

In a preferred embodiment of the invention the bottle 20 is made from a mixture of plastics material (such as polypropylene) and a flux material. The bottle typically comprises 60 to 80% calcium carbonate and 40 to 20% polypropylene. The advantages of including flux with the plastics material is discussed below.

The flux 26 comprises:

WO 00/26664

PCT/IB99/01747

- 11 -

20% to 60%, preferably 25% to 40%, by weight, sodium hydroxide (NaOH);

20% to 60%, preferably 25% to 40%, by weight, lead oxide;

20% to 60%, preferably 25% to 40%, by weight, borax; and

may also contain a small amount (0 to 1%) of silver nitrate.

Each bottle 20 contains a predetermined charge and constitution of flux. The bottles are conveniently filled with flux on a production line at a production site and then transported to the site at which assaying takes place. The charge of flux, which varies from 200 to 450g, depends on the amount and type of sample being assayed. Generally, there is a ratio of flux to sample of 4:1 to 6:1, by weight. The constitution of the flux depends on the characteristics of the sample being assayed. For example, a higher amount of borax is added for samples containing higher concentrations of base metals and a higher amount of sodium hydroxide is added for samples containing high amounts of silicates.

It is important that the lid 22 engages sealingly with the opening to the bottle 20 to ensure that the sodium hydroxide (NaOH) which is corrosive and hygroscopic does not come into contact with the atmosphere during transportation and storage of the bottle and flux.

In the process, the lid 28 of the bottle 20 is removed an aliquot sample of ore is added to a bottle 20 containing flux 26, the lid 28 is applied back onto the bottle 20 and the sample and flux is combined by merely shaking the bottle.

10/24/01 16:33 FAX +27 11 3157445 JOHN AND KERNICK

WO 00/26664

PCT/IB99/01747

- 12 -

Previously, mixing containers were used which caused spillages and contamination between samples. Thus, the bottle 20 conveniently provides a package containing a required charge of flux which is also used to combine the aliquot sample and the flux.

It is envisaged that the sample preparation step is automated as a series of mechanically linked steps, enabling the preparation of an ore sample for assaying without the need for manual intervention.

Referring to Figure 3, bottles 20 which contain ore sample combined with flux are loaded onto a sample loader 34 which comprises a conveyor belt 36, an optical sensor 38, a bar code reader 40, and a mechanical gripper arm 42. In use, the optical sensor 38 senses the presence of a bottle 20, the bar code reader 40 (positioned above the bottle, and shown in dotted outline) scans the bar code 28 on the lid of the bottle 20 and the gripper arm 42 grips the bottle at the ridge 30 and transfers it into an induction furnace 44 which is powered by a generator 46. The conveyor 36 conveys the next bottle 20 in line with the sensor 38 and this next bottle is then ready to be transferred into the induction furnace 44. Once placed in the induction furnace 44, the identity of the bottle 20 is compared to the information stored on the central database and the bottle 20 is heated at a temperature profile that corresponds to the ore sample and flux contained within the bottle 20.

Referring to Figure 4, the induction furnace 44 includes a removable melting pot 46 for melting the sample and flux. The melting pot 46 may be made from any material that can sustain temperatures of up to 1500°C and which is not adversely affected by electromagnetic waves from an induction coil. For example, graphite or zirconium may be used. Zirconium is

WO 00/26664

PCT/IB99/01747

- 13 -

preferred because it is resistant to sodium hydroxide fusions and does not oxidise as readily as graphite at high temperatures. Zirconium also has a high melting point of 1850°C, well above the operation temperatures of the induction furnace. It is important that the temperature of the melting pot 46 is monitored and thermocouples 49 are provided on the melting pot 46 for this purpose. The melting pot 46 is surrounded by a barrier 47 of ceramic material (1600 heat isolating) which in turn is surrounded by an induction coil 48. The induction coil 48 is surrounded by a shunt 51 that directs electromagnetic waves from the coil 48 toward the melting pot 46. The abovementioned components are housed in a housing 50 which is made from a ceramic material (polyester board GPO3). The furnace 44 also has a lid 52 which has a backing 54 also made from the ceramic material and an underside 56, made from alumina or zirconia based ceramic material, which closes the opening 58 into the melting pot 46, when the lid 52 is closed. It is important that the lid 52 closes the melting pot 46 sufficiently to create a reducing atmosphere therein to minimize oxidation of the melting pot 46 at the high temperatures within the furnace.

Once a bottle 20 has been inserted into the melting pot 46 the lid 52 is closed, and the bottle 20 and mixture of sample and flux therein are heated according to a predetermined temperature profile which is controlled by the amount of power applied to the induction coil. The temperature profile may be selected according to the amount and characteristics of ore which is being assayed and also the amount and characteristics of the flux 26.

In a typical example where the temperature profile is kept constant, the melting pot 26 is heated to about 900° and the flux and sample is inserted into the melting pot 26. The coil 48 is supplied with 15-30 kW of electrical

WO 00/26664

PCT/IB99/01747

- 14 -

energy from the generator 46 for a predetermined first period of time (usually 20 to 30 seconds) to heat the pot to about 1250°C and then dropped to 10 to 12kW for a predetermined second period of time (usually 20 to 30 seconds), maintaining the temperature of the melting pot at about 1250°C. Thus, fusion of the ore and flux takes from 45 to 90 seconds, generally approximately 60 seconds.

If necessary, the sample and flux may be heated at a predetermined varied temperature profile, for example by first heating the flux and sample to about 1250°C for a first period of time (20 - 30 seconds) to melt the sample and flux and to then decreasing the temperature to about 1000°C for a second period of time (20 - 30 seconds), while the gold and PGMs are collected by the lead.

Another important aspect of the invention is that the temperature profile applied to each sample can be computer-controlled and thus the heating conditions can be accurately controlled, according to the identification made by the bar code reader. Information on each sample, such as sample type, sample weight, flux weight, flux composition, fusion conditions (i.e. temperature profile) is stored on a central database. Each sample is identified before it is added to the furnace and it is then heated according to a predetermined temperature profile. The system can also be used to subject similar ores, or ores from the same area, to similar or the same conditions, to ensure consistent assay results.

Fusion of the ore and flux is extremely quick and the alternating electromagnetic waves (eddy waves) from the induction coil causes a violent stirring action of molten lead within the crucible which results in complete

T02240" 550E50

WO 00/26664

PCT/IB99/01747

- 15 -

collection of gold and PGMs by the lead within about 60 seconds of power being applied to the induction furnace.

During heating, the temperature of the melting pot must be monitored by the thermocouples 49 and by altering the energy applied to the induction coil 48 to ensure that the temperature of the molten lead and flux remains within a preferred temperature range of between 1150 °C and 1300°C. If the temperature exceeds 1450°C chrome III within the sample will be converted to chrome V and the chrome metal formed can trap gold and PGM's and negatively affect results. If the temperature drops too low (below 900°C), the slag will begin to solidify and it is then difficult to separate the slag from the lead.

The ceramic housing 50 ensures that, while the temperature within the crucible 46 can reach up to 1400°C, the outer surface of the ceramic housing 50 does not reach more than 60 to 100°C. This is because the ceramic housing 50 is not heated by eddy waves from the induction coil 48. The ceramic barrier 47 (which is not heated by the induction coil) serves to insulate the crucible 46 so that radiant energy is isolated within the crucible.

The advantage of the flux 26 over known flux compositions is that the sodium hydroxide has a melting point of 318°C, which is much lower than the melting point of  $\text{CaCO}_3$ , used in conventional fire assay processes. Thus, when the flux 26 is added to the crucible 46 in the induction furnace 46 (which is normally preheated a temperature of about 1000°C), the sodium hydroxide melts, wets the sample and flux, and retards spattering and boiling when power is applied to the induction furnace. The sodium hydroxide then reacts with silicates in the sample to form slag. Up to now it

T02240" E580850

WO 00/26664

PCT/IB99/01747

- 16 -

has not been possible to use sodium hydroxide in conventional fire assay processes as these processes make use of clay pots and the sodium hydroxide would react with silica in the pots and destroy them during heating. The sodium hydroxide does not however have this effect on a graphite or zirconium melting pot 46. Also, there has been no feasible way of storing and transporting NaOH, because it is hygroscopic, and the sealed containers address this problem. Furthermore, fire assay flux used in the past containing calcium carbonate cannot be used in an induction furnace as it will blow out during rapid heating of the melting pot 46.

Thus, the flux 26, comprising sodium hydroxide makes it possible to rapidly melt an ore sample in an induction furnace as described above without losing flux and ore sample in the process.

The plastics bottle 20 is also an important part of the heating process as it provides a carbon source for reducing the lead oxide to produce molten lead. The inclusion of flux (calcium carbonate) with the plastic is to replace excess plastic which is merely burnt away, and to reduce flames and smoke during heating.

Referring back to Figure 3, after the sample has been heated in the induction furnace 44, the molten sample, which comprises lead containing gold and PGM's from the sample, and slag, is separated.

The mixture of slag and lead may be poured from the melting pot 46 into another receptacle and the lead and slag separated in that receptacle. However, according to a preferred embodiment of the invention, the melting pot 46 also performs the function of separating the molten lead from the

093085.0424



Figure 5 shows a melting pot 46 which is arranged to be received in an induction furnace, and which serves the dual purpose of separating molten lead from slag. As discussed above, the melting pot 46 may be made from a material such as graphite or zirconium. Zirconium is preferred as molten lead does not adhere to the heated zirconium. This is advantageous as the melting pot 46 is intended to be used for numerous samples and this limits the contamination of subsequent samples from previous samples.

Referring to Figure 6, the melting pot 46 comprises a base 60 with a side wall 62 extending from the base and defining a top opening 64. A first spout 66 is provided at the top opening 64 for decanting molten material from a melting zone 68 within the melting pot 46. A second spout 70 is provided at the top opening 64 and is diametrically opposed to the first spout 66.

A collector 72 defining a collecting cavity 76 is provided on the side wall 62 of the melting pot 46. below the first pouring spout 66. The collector 72 may be formed integrally with the pot but is preferably removable in the form of an externally threaded plug which screws into a complimentary threaded aperture 74 in the side wall 62. The collecting cavity 76 is sized to accommodate only a predetermined amount of molten lead (i.e. the amount of lead in a molten assay sample). In a typical example, the collecting cavity 76 is sized to accommodate only 64 grams of lead from a flux containing 70 grams of lead oxide. Depending on the amount of lead in a molten sample the cavity 76 may be selected to contain from 35 to 110 grams of lead. The removable plug is advantageous as different size

WO 00/26664

PCT/IB99/01747

- 18 -

collecting cavities 76 can be selected and provided for different samples that are being assayed. This is important as the zirconium melting pot 46 is expensive to manufacture. The collector 72 is located proximate the top opening 64, and away from the melting zone 68, where the pot is corroded during fusion, so that the collector is not damaged during fusion.

In addition to what is stated above, the plug 72 has a side wall 78 which protrudes from the side wall 62 of the side wall 62 of the melting pot 46. The side wall 78 is advantageous as it provides a barrier that helps to collect lead in the collecting cavity 76.

As mentioned above, it is important to monitor the temperature of the melting pot 46 during operation and thermocouples 80 are provided in the base 60 of the melting pot 46, for this purpose.

Once the sample and flux have been fused to provide a slag and when the gold and PGM's have been collected in the molten lead, the molten lead and slag are separated by rotating the melting pot 46 to tip firstly the slag and then secondly and separately the lead from the melting pot 46. In this embodiment of the invention the melting head is not removed from the furnace and separation is conveniently achieved by tipping the whole of the induction furnace, i.e. tipping the induction coil together with the melting pot 46.

Referring to Figure 7, after a sample and flux have been fused, in a melting pot 46 in an induction furnace 44, the furnace 44 is rotated in a first direction "A" toward the first spout 66 and the lead collector 72. The furnace 44 is rotated through approximately 160°. Because of different

TO: 24/04 '01 TUE 16:35 FAX +27 11 3157445 JOHN AND KERNICK

WO 00/26664

PC/IB99/01747

- 19 -

densities and viscosities, slag 80 is poured out of the melting pot 46 via the first spout 66 and all of the molten lead 82 is trapped in the lead collector 72. The side wall 78 of the collector 72 forms a barrier that protrudes from the side wall of the melting pot 46 and assists in the collection of the molten lead.

The slag that is poured out of the melting pot 46 is poured into a waste bin (not shown). After all of the slag has discharged from the melting pot 46, the furnace is rotated back into an upright position.

The furnace 44 is then rotated in a second direction "B" which is opposite to the first direction "A", also through about 160°. Molten lead 84 within the melting pot 46 is then discharged out of the melting pot 46, via the second spout 70 into a water-cooled mould 86.

It is important to keep the melting head 46 at a temperature above 900°C during the above process so that the molten lead and slag are properly separated and so that molten lead is not left behind within the melting head 46. In this regard, the induction coil 48 extends to the spouts 68 and 70 to heat them and ensure that they do not cool to below 900°C.

The mould 86 is water-cooled to about 10°C and the molten lead poured into the mould solidifies within about 5 to 10 seconds to form a lead button.

Rapid cooling of the molten lead stops gold and PGMs in the lead from forming layers ensuring that the concentration of gold and PGMs within the lead button is homogenous.

TO:240"5430360

WO 00/26664

PCT/IB99/01747

- 20 -

Thereafter, the button is removed from the mould and stamped with an identification number which corresponds to the bar code which was read at the beginning of the process and the buttons are stored on a button storage rack, ready to be analyzed.

The amount of gold and PGMs within the button may be analysed by any conventional processes, for example by cupellation or lead dissolution. The lead cupellation processes takes approximately 2,5 hours to perform and the lead dissolution process takes approximately 8 hours to perform. The main advantage of homogenous button 74 produced by the process of the invention is that it can be analysed by way of much quicker processes such as spark analysis and laser ablation. In prior art processes, due to the separation and cooling techniques employed, PGMs and gold form layers within the lead and the lead cannot be analysed by spark analysis or laser beam ablation. As spark analysis and laser ablation only takes approximately 30 seconds, the use of these processes on the lead buttons produced by the invention dramatically reduces the time taken up by analysis. By using spark analysis or laser ablation, the whole fire assay and analysis process could be done in far less time than the twelve hour turn around time of known processes.

In addition to the above advantages, the fire assay method and apparatus according to the invention provides a much more comfortable working environment than the hot and uncomfortable working environment of prior art furnaces. The apparatus according to the invention also takes up far less work space and means that assay laboratories are more financially viable. Furthermore, the system requires less power than prior art processes and reduces replacement parts such as elements, clamps and braids for furnaces,

T02240 5930360

WO 00/26664

PCT/IB99/01747

- 21 -

loading and pouring equipment and clay crucibles. Lastly, the apparatus and process of the invention can provide an automated process that is not labour intensive.

#### Example1

A typical charge of flux according to the invention for analyzing 5g concentrate ore samples from a reef in Rustenburg in South Africa, to test for platinum, palladium, rhodium and gold has the following amount and composition:

80g Borax  
85g Litharge  
45g NaOH

The flux is provided in a sealed plastic bottle. The bottle has a receptacle portion that weighs from 35 to 45g and a lid that weighs  $\pm 10$ g. The lid is made from polyethylene and the receptacle is made from 40%, by weight, polypropylene and 60%, by weight, calcium carbonate.

#### Example2

A typical charge of flux according to the invention for analyzing 75g feed ore samples from a reef in Rustenburg in South Africa, to test for platinum, palladium, rhodium and gold has the following amount and composition:

80g Borax  
85g Litharge

TO 4249 5530E860

WO 00/26664

PCT/IB99/01747

- 22 -

60g NaOH

The flux is provided in a sealed plastic bottle. The bottle has a receptacle portion that weighs from 50 to 60g and a lid that weighs  $\pm 10$ g. The lid is made from polyethylene and the receptacle is made from 40%, by weight, polypropylene and 60%, by weight, calcium carbonate.

#### Example 3

A typical charge of flux according to the invention for analyzing 100g tail ore samples from a reef Rustenburg in South Africa, to test for platinum, palladium, rhodium and gold has the following amount and composition:

160g Borax

85g Litharge

140g NaOH

The flux is provided in a sealed plastic bottle. The bottle has a receptacle portion that weighs from 60 to 75g and a lid that weighs  $\pm 10$ g. The lid is made from polyethylene and the receptacle is made from 40%, by weight, polypropylene and 60%, by weight, calcium carbonate.

#### Example 4

This Example shows a typical method according to the invention, in which feed ore samples from a mine in Rustenburg, South Africa, were analyzed. Feed ore samples were prepared by drying feed tail ore, comminuting and sieving it, and weighing aliquot samples of 75g of ore.

WO 00/26664

PCT/IB99/01747

- 23 -

The lid of a sealed container as described in Example 2 and containing a flux composition according to Example 2 was opened. An aliquot ore sample was added to the container and the lid was replaced. The container was then shaken to combine the ore sample and the flux composition.

The container was then inserted into a triple pitch impregnated graphite pot which was surrounded by an induction coil in an induction furnace. The induction coil was powered by a 15kW induction generator.

The graphite pot had been pre-heated to 1250°C. Once the bottle had been inserted into the melting pot, the lid of the furnace was closed and the heat of the pot was maintained at 1250°C for 90 seconds, by applying 15kW of power to the coil at 6.5kHz. Although it is possible and sometimes advantageous to heat the sample according to a varied temperature profile, the temperature in this example was kept constant at 1250°C during melting and fusion.

After 90 seconds the power to the induction furnace was reduced and the molten sample of lead and slag were poured into and separated in a heated separator as described in South African provisional patent application no. 99/1831 which is incorporated herein by reference.

The separated molten lead was poured into a chilled mould and formed into a solid lead button within 10 seconds.

The above process was carried out with 10 aliquot samples of ore. The solid lead buttons were then analyzed by cupellation and lead dissolution methods and the results of the analysis are set out in Table 1 below:

FOUO 2004 09 03 15:00

PCT/IB99/01747

Induction									
Lead dissolution					Cupellation				
Pt	Pd	Rh	Au	4T	Pt	Pd	Rh	Au	4T
2.03	2.28	0.198	0.293	4.80	2.32	2.42	0.188	0.380	5.31
2.17	2.37	0.198	0.285	5.02	2.25	2.27	0.188	0.275	4.98
2.03	2.33	0.198	0.280	4.84	2.15	2.26	0.188	0.258	4.86
2.14	2.27	0.193	0.283	4.89	2.1	2.34	0.188	0.300	4.93
2.12	2.38	0.195	0.278	4.97	2.08	2.28	0.180	0.275	4.82
2.17	2.39	0.193	0.285	5.04	2.41	2.32	0.180	0.298	5.21
2.37	2.25	0.185	0.343	5.15	2.02	2.29	0.190	0.333	4.83
2.07	2.33	0.198	0.233	4.83	2.23	2.4	0.193	0.268	5.09
2.20	2.41	0.203	0.293	5.11	2.07	2.31	0.185	0.268	4.83
2.13	2.27	0.190	0.343	4.93	2.07	2.25	0.190	0.275	4.79
2.14	2.33	0.195	0.292	4.96	2.17	2.31	0.19	0.29	4.96
4.4	2.4	2.5	10.4	2.3	5.6	2.4	2.1	12.2	3.5
2.10	2.31	0.208	0.246	4.86	2.10	2.31	0.208	0.246	4.86

Avg  
%RSD  
NiS Consensus

The same feed sample was tested in a nickel sulphide fire assay process known in the prior art. The results of these tests are set out in Table 2 below:

Fire Assay									
Lead dissolution					Cupellation				
Pt	Pd	Rh	Au	4T	Pt	Pd	Rh	Au	4T
1.57	1.73	0.140	0.270	3.71	1.87	1.75	0.135	0.190	3.95
2.14	1.94	0.160	0.260	4.50	1.73	1.78	0.140	0.200	3.85
1.66	1.71	0.150	0.250	3.77	1.77	1.86	0.145	0.185	3.96
1.84	1.96	0.160	0.220	4.18	1.98	1.99	0.153	0.260	4.38
2.08	2.11	0.190	0.250	4.63	2.39	2.21	0.170	0.288	5.06
2.03	2.14	0.180	0.280	4.63	1.97	2.01	0.158	0.318	4.46
1.94	2.05	0.180	0.460	4.63	1.97	2.15	0.163	0.260	4.54
2.07	2.14	0.190	0.230	4.63	1.96	2.25	0.173	0.250	4.63
2.03	2.21	0.180	0.300	4.72	2.37	2.3	0.170	0.260	5.10
2.23	2.32	0.200	0.280	5.03	2.23	2.2	0.180	0.253	4.86
1.96	2.03	0.173	0.280	4.44	2.02	2.05	0.159	0.246	4.48
10.2	9.2	10.7	22.9	9.1	10.9	9.3	9.1	16.5	9.6
2.10	2.31	0.208	0.246	4.86	2.10	2.31	0.208	0.246	4.86

Avg  
%RSD  
NIS Consensus



- 25 -

From Tables 1 and 2 it is clear that the results of the lead buttons prepared in the induction heating process according to the invention compare very well with the results the lead buttons prepared by the nickel sulphide fire assay process. In fact, the RSD for the induction process is significantly lower than that of the nickel sulphide fire assay process.

#### Example 5

Lead buttons from an ore sample, prepared by a process according to the invention as described in Example 4 were tested by spark analysis and were found to provide accurate results.

A tail sample from a reef in Rustenburg South African was treated in the same way as described in Example 4 to produce three lead buttons. The buttons were analysed by spark analysis and the results are set out below:

Pt	Pd	Rh	Au	Total PGM
0.53	0,20	0,07	0,07	0,87
0.54	0,19	0,06	0,04	0,83
0.55	0,19	0,06	0,04	0,84

Conventional cupellation techniques were carried out on lead buttons from the same sample and revealed a total PGM value of 0,82 grams per ton.

#### Example 6

The process according to the invention as described in Example 4 was carried out using a melting pot made of zirconium, except the ore sample

**WO 00/26664**

PCT/IB99/01747

- 26 -

was replaced with silica. After fusion, it was found that the zirconium melting pot is superior to the graphite melting pot in that it did not oxidise as much at high temperatures as the graphite pot, and the molten lead does not adhere as much to the zirconium pot.

[illegible]

WO 00/26664

PCT/IB99/01747

27.

## CLAIMS

1. A method for assaying an ore sample to determine the concentration of selected metals therein, comprising the steps of:

combining the prepared ore sample with a lead-containing flux in a receptacle;

inductively heating the combination to form a fusion of slag and lead containing the metals in the sample; and

separating the lead from the slag.

2. The method according to claim 1 wherein the combination is heated at a predetermined temperature profile.

3. The method according to claim 2 wherein the predetermined reference temperature profile is determined by the characteristics and amount of the ore sample and/or the flux.

4. The method according to claim 3 wherein the sample is supplied with a high level of heat for a predetermined first period of time and then supplied with a lower level of heat for a predetermined second period of time to form the fusion of slag and lead.

5. The method according to any one of the preceding claims wherein the sample of ore and flux are combined in a container made from carbon-based material, and the container, the sample and the flux are inductively heated.

093099-04201

9. APR. 2001 15:48

LPA MUENCHEN 089/2399-4465

NR. 039

S. 11

WO 00/26664

PCT/IB99/01747

28

6. The method according to claim 5 wherein the container is made from plastics material and comprises a lid which is arranged to close the container sealingly.

7. The method according to claim 5 or 6 wherein the container includes identification means for identifying the sample contained therein.

8. The method according to claim 7 wherein the identification means is a barcode.

9. A method according to any one of the preceding claims wherein the flux contains sodium hydroxide.

10. The method according to any one of the preceding claims wherein the sample is heated inductively within a graphite melting pot [receptacle] in an induction furnace.

11. The method according to any one of the preceding claims wherein the sample is heated inductively within a zirconium melting pot [receptacle] in an induction furnace.

12. The method according to any one of the preceding claims wherein molten lead separated from the slag is poured into a chilled mould, to provide a solid lead button.

13. A method according to claim 5 including the steps of storing information on each sample on a central database, providing each container into which the sample is poured with a unique identification means,

09330855 042704

WO 00/26664

PCT/IB99/01747

29

identifying each container before inserting it into the induction furnace, correlating the identity of the container and information on the central database, and applying a predetermined reference temperature profile to the sample, according to the information on the sample stored in the database.

14. A method according to claim 13 wherein the identification means is a bar code and the bar code is identified with a scanner.

15. A method according to any one of the preceding claims wherein each solid lead button is stamped with an identification code.

16. A receptacle for use in a method for assaying an ore sample according to claim 1, the receptacle comprising a base with a side wall extending from the base, the side wall defining a top opening into the receptacle, and the side wall having a collecting cavity, wherein the collecting cavity is sized to collect a predetermined amount of molten lead.

17. A receptacle for use in a method for assaying an ore sample according to claim 16 wherein the collecting cavity is located proximate the top opening of the receptacle.

18. A receptacle for use in a method for assaying an ore sample according to claim 16 or 17 wherein barrier means is provided between the collecting cavity and the opening of the receptacle, to trap molten lead in the collecting cavity.

19. A receptacle for use in a method for assaying an ore sample according to

09330665.042794

WO 00/26664

PCT/IB99/01747

30

any one of claims 16 to 18 wherein the collecting cavity is formed within a removable plug which is attachable to the side wall of the receptacle.

20. A receptacle for use in a method for assaying an ore sample according to any one of claims 16 to 19 including a first spout located at the top opening, above the collecting cavity.

21. A receptacle for use in a method for assaying an ore sample according to claim 20 including a second spout located at the top opening, diametrically opposed to the first spout.

22. A receptacle for use in a method for assaying an ore sample according to any one of claims 16 to 21 wherein the receptacle is also a melting pot for an induction furnace.

23. A receptacle for use in a method for assaying an ore sample according to any one of claims 16 to 22 made from graphite.

24. A method for separating molten lead from slag, in the receptacle of claim 16, the method including the steps of:

1. introducing a slag with a predetermined amount of molten lead therein into the receptacle;
2. rotating the receptacle in a first direction toward the collecting cavity so that the molten lead fills and is retained within the cavity, rotating the receptacle further so that the slag is discharged from the opening to the receptacle;

TO 2240 550950

WO 00/26664

PCT/IB99/01747

31

3. rotating the receptacle so that the molten lead flows out of the opening to the receptacle; and
4. collecting the lead discharged from the opening of the receptacle.

5. A method according to claim 24 wherein the receptacle is a melting pot surrounded by an electromagnetic coil and the electromagnetic coil is rotated together with the melting pot.

---

26. A flux composition for use in a method for assaying an ore sample according to claim 1, the flux composition containing sodium hydroxide.

27. A flux composition for use in a method for assaying an ore sample according to claim 26, comprising 20% to 60%, by weight, sodium hydroxide.

28. A flux composition for a method for assaying an ore sample according to any one of claims 26 to 27 further comprising:

20% to 60%, by weight, lead oxide; and  
20% to 60%, by weight, borax.

29. A flux composition for use in a method for assaying an ore sample according to claim 27 comprising 20% to 50%, by weight sodium hydroxide, 25% to 40% lead oxide and 25% to 40% borax.

30. A flux composition for use in a method for assaying an ore sample

T02240 990360

9. APR. 2001 15:49

MUNICHEN 089/2399-4465

NR. 039

S. 15

WO 00/26664

PCT/IB99/01747

32

according to any one of claims 26 to 29 further including silver nitrate.

31. A sealed container, for use in a method for assaying in an ore sample according to claim 5, the sealed container made from a carbon-based sodium carbonate.

32. A sealed container for use in a method for assaying an ore sample according to claim 31 including a replaceable lid.

33. A sealed container for use in a method for assaying an ore sample according to claim 31 or 32 made from a combustible material.

34. A sealed container for use in a method for assaying an ore sample according to claim 33 made from a plastics material.

35. A sealed container for use in a method for assaying an ore sample according to claim 34 made from a mixture of plastics material and a flux material.

36. A sealed container for use in a method for assaying an ore sample according to claim 35 wherein the flux material is calcium carbonate.

37. A [sealed container for use in a method for assaying an ore sample according to claim 36, the mixture including 60 to 80%, by weight, calcium carbonate.

T02240" 05300050



WO 00/26664

09/830855

PCT/IB99/01747

1/4

FIG 1




FIG 2





FIG 3




09/830855

PCT/IB99/01747

WO 00/26664

2/4






09/830855

PCT/IB99/01747

WO 00/26664

4/4



Page 1

Attorney's Docket No. \_\_\_\_\_

**DECLARATION - USA PATENT APPLICATION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name;

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled "ASSAYING"

the specification of which:

- (a) ☒ is attached hereto; or
- (b) ☐ was filed on \_\_\_\_\_ as Application No. 0 / \_\_\_\_\_ or Express Mail No., as Application No. not yet known \_\_\_\_\_ and was amended on \_\_\_\_\_ (if applicable); or
- (c) ☒ was described and claimed in PCT International Application No. PCT/IB99/01747 filed on 29.10.1999 and as amended under PCT Article 19 on \_\_\_\_\_ (if any) and/or under PCT Article 34 on \_\_\_\_\_ (if any).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above;

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, § 1.56;

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 of any foreign application(s) for patent, design or inventor's certificate or any PCT international application(s) listed below and have also identified below any foreign application(s) for patent, design or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed for the same subject matter having a filing date before that of the application(s) of which priority is claimed:

**PRIOR FOREIGN APPLICATION(S)**

COUNTRY (OR INDICATE IF PCT)	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 37 U.S.C. § 119
ZA	98/9866	29.10.1998	<input checked="" type="checkbox"/> YES NO <input type="checkbox"/>
			<input type="checkbox"/> YES NO <input type="checkbox"/>
			<input type="checkbox"/> YES NO <input type="checkbox"/>
			<input type="checkbox"/> YES NO <input type="checkbox"/>
			<input type="checkbox"/> YES NO <input type="checkbox"/>

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below, and insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56(a)

0933035-0449-5920E350

Page 2

Attorney's Docket No. \_\_\_\_\_

Prior U.S.A. Application(s)

Application No.: \_\_\_\_\_ Filing Date: \_\_\_\_\_ Status: \_\_\_\_\_

POWER OF ATTORNEY: I hereby appoint the registrants of Knobbe, Martens, Olson & Bear, LLP, 620 Newport Center Drive, Sixteenth Floor, Newport Beach, California 92660, Telephone (949) 760-0404, Customer No. 20,995.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful, false statements may jeopardize the validity of the application or any patent issued thereon.

-----  
Full name of sole or first inventor: WILLEM H BRITSInventor's signature Willem H Brits Day 24 Month 04 Year 2001Residence (city and country): BRAKPAN, GAUTENG PROVINCE, REPUBLIC OF SOUTH AFRICA ZAXCitizenship: SOUTH AFRICANPost Office Address: 20 Boekenhout Street, Dalpark Ext 5, Brakpan, Gauteng Province,  
Republic of South Africa

Full name of second inventor: \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Day \_\_\_\_\_ Month \_\_\_\_\_ Year \_\_\_\_\_

Residence (city and country): \_\_\_\_\_

Citizenship: \_\_\_\_\_

Post Office Address: \_\_\_\_\_

Full name of third inventor: \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Day \_\_\_\_\_ Month \_\_\_\_\_ Year \_\_\_\_\_

Residence (city and country): \_\_\_\_\_

Citizenship: \_\_\_\_\_

Post Office Address: \_\_\_\_\_

Send Correspondence To:

KNOBBE, MARTENS, OLSON &amp; BEAR, LLP

04240550350000